

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (1) Washed Rock Salt</b>		
<b>Traceable to</b>	: 1. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	3. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

**Test results**

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>0.55</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>99.61</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.08</b>	%	ASTM E534-03
4	Ca ++		<b>0.05</b>	%	ASTM E534-03
5	Mg ++		<b>0.02</b>	%	ASTM E534-03
6	SO4 -		<b>0.16</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.17</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.05</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.04</b>	%	ASTM E534-03
10	Fe		<b>5</b>	ppm	AAS

-----End of Report-----

**Authorized Signature:**  
**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.


<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 2 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (2) Washed Rock Salt</b>		
<b>Traceable to</b>	: 2. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	4. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

**Test results**

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>0.37</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>99.54</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.09</b>	%	ASTM E534-03
4	Ca ++		<b>0.03</b>	%	ASTM E534-03
5	Mg ++		<b>0.05</b>	%	ASTM E534-03
6	SO4 -		<b>0.18</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.10</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.13</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.09</b>	%	ASTM E534-03
10	Fe		<b>5.5</b>	ppm	AAS

-----End of Report-----

**Authorized Signature:**  
**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

**GENERAL CONDITIONS**

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (3) Washed Sea Salt</b>		
<b>Traceable to</b>	: 3. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	5. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

**Test results**

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>1.50</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>99.53</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.05</b>	%	ASTM E534-03
4	Ca ++		<b>0.07</b>	%	ASTM E534-03
5	Mg ++		<b>0.03</b>	%	ASTM E534-03
6	SO4 -		<b>0.19</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.24</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.03</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.10</b>	%	ASTM E534-03
10	Fe		<b>4.5</b>	ppm	AAS

-----End of Report-----

**Authorized Signature:**  
**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

Courtyard Complex, Sheikh Zayed Cairo, Egypt Tel. 062 3 218 985 <b>Head office - Licensee No. 13822</b>	Tout Ankh Amount Towers, Kiroseiz, 3 <sup>rd</sup> Floor, Office No. 307, Alexandria, Egypt - Tel. 03 42 30395 <b>Back-office</b>	K25 Cairo/Alex Road, Merghim, Behind Toyota, Alexandria, Egypt Tel. 03 47 00181 <b>Central Laboratory</b>	City Star October - Building no. 2 Third floor 6 of October City, Egypt <b>Food Laboratory</b>
--	--	--	---

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (5) Deicing Rock Salt</b>		
<b>Traceable to</b>	: 5. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	7. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

### Test results

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>0.57</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>98.53</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.93</b>	%	ASTM E534-03
4	Ca ++		<b>0.07</b>	%	ASTM E534-03
5	Mg ++		<b>0.06</b>	%	ASTM E534-03
6	SO4 --		<b>0.23</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.24</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.08</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.17</b>	%	ASTM E534-03

-----End of Report-----

**Authorized Signature:**  
**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

Page 5 of 7

Courtyard Complex, Sheikh Zayed  
Cairo, Egypt  
Tel. 062 3 218 985  
**Head office - Licensee No. 13822**

Tout Ankh Amount Towers, Kiroseiz,  
3<sup>rd</sup> Floor, Office No. 307, Alexandria,  
Egypt - Tel. 03 42 30395  
**Back-office**

K25 Cairo/Alex Road, Merghim,  
Behind Toyota, Alexandria, Egypt  
Tel. 03 47 00181  
**Central Laboratory**

City Star October - Building no.  
2 Third floor 6 of October City,  
Egypt  
**Food Laboratory**

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (4) Washed Sea Salt</b>		
<b>Traceable to</b>	: 4. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	6. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

### Test results

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>2.54</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>99.41</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.06</b>	%	ASTM E534-03
4	Ca ++		<b>0.07</b>	%	ASTM E534-03
5	Mg ++		<b>0.06</b>	%	ASTM E534-03
6	SO4 --		<b>0.21</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.24</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.05</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.19</b>	%	ASTM E534-03
10	Fe		<b>3.9</b>	ppm	AAS

-----End of Report-----

**Authorized Signature:**  
**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Tablet Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Sample (8) Tablet Salt</b>		
<b>Traceable to</b>	: 6. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	: 8. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

### Test results

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>0.10</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>99.12</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.08</b>	%	ASTM E534-03
4	Ca <sup>++</sup>		<b>0.12</b>	%	ASTM E534-03
5	Mg <sup>++</sup>		<b>0.04</b>	%	ASTM E534-03
6	SO4 <sup>-</sup>		<b>0.23</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.33</b>	%	ASTM E534-03
8	CaCl <sub>2</sub>		<b>0.07</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.35</b>	%	ASTM E534-03

-----End of Report-----

Authorized Signature:

Lab Manager: Ahmed Osama



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

Page 6 of 7

Courtyard Complex, Sheikh Zayed  
Cairo, Egypt

Tel. 062 3 218 985

Head office - Licensee No. 13822

Tout Ankh Amount Towers, Kiroseiz,  
3<sup>rd</sup> Floor, Office No. 307, Alexandria,  
Egypt - Tel. 03 42 30395

Back-office

K25 Cairo/Alex Road, Merghim,  
Behind Toyota, Alexandria, Egypt  
Tel. 03 47 00181

Central Laboratory

City Star October - Building no.  
2 Third floor 6 of October City,  
Egypt

Food Laboratory

<b>Sampled by</b>	: <input type="checkbox"/> Operation team	<input checked="" type="checkbox"/> <b>Client</b>	<input type="checkbox"/> Other
<b>Analyses</b>	: <b>Received: 22/06/2026</b>	<b>Analysis: 22/06/2026</b>	
<b>Type of sample:</b>	: <b>Salt</b>		
<b>Approx. Weight:</b>	: 0.5 Kg		
<b>Packaging:</b>	: Plastic bag and sealed not with TUV seal no.		
<b>Vessel</b>	: --	<b>Booking No.:</b>	
<b>Others:</b>	: Sub Lot / Composite/ <b>Received</b> / Retained:		
<b>Received condition</b>	: <b>Deicing Rock Salt</b>		
<b>Traceable to</b>	: 7. Analysis balance. #Inv. C008	2. Analysis balance.	#Inv.C009
	: 9. Oven. #Inv. C006	4. Muffle.	#Inv.C003
<b>Lab. Room</b>	: Temperature (24 ° C)	Humidity (53)	

**Test results**

Ser.	Test Name	Specs	Results	Unit	Ref./issue year
1	Moisture		<b>0.53</b>	%	ASTM E534-03
2	Purity (as sodium chloride)		<b>98.58</b>	%	ASTM E534-03
3	Water Insoluble Matter		<b>0.96</b>	%	ASTM E534-03
4	Ca ++		<b>0.06</b>	%	ASTM E534-03
5	Mg ++		<b>0.05</b>	%	ASTM E534-03
6	SO4 -		<b>0.20</b>	%	ASTM E534-03
7	CaSO <sub>4</sub>		<b>0.20</b>	%	ASTM E534-03
8	MgSO <sub>4</sub>		<b>0.07</b>	%	ASTM E534-03
9	MgCl <sub>2</sub>		<b>0.14</b>	%	ASTM E534-03

-----End of Report-----

**Authorized Signature:**

**Lab Manager: Ahmed Osama**



**This report** is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

**The information** stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice.

**This report** reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested.

Courtyard Complex, Sheikh Zayed Cairo, Egypt Tel. 062 3 218 985 <b>Head office - Licensee No. 13822</b>	Tout Ankh Amount Towers, Kiroseiz, 3 <sup>rd</sup> Floor, Office No. 307, Alexandria, Egypt - Tel. 03 42 30395 <b>Back-office</b>	K25 Cairo/Alex Road, Merghim, Behind Toyota, Alexandria, Egypt Tel. 03 47 00181 <b>Central Laboratory</b>	City Star October - Building no. 2 Third floor 6 of October City, Egypt <b>Food Laboratory</b>
--	--	--	---